## **CARTER ENS-EP 700**



Lubrication



## Lubricant coating for open gears wire ropes.

APPLICATIONS	
Exposed gears and cables	<ul> <li>CARTER ENS/EP 700 is used for lubricating:</li> <li>Open gears rotating at low speed and high power</li> <li>Ring gears</li> <li>Racks and guide rails</li> <li>Wire ropes and chains.</li> <li>CARTER ENS/EP 700 is made fluid by a volatile solvent to facilitate application (as an aerosol).</li> </ul>
SPECIFICATIONS	]
International specifications	<ul> <li>NF-ISO 8743-6 category CKJ</li> </ul>
ADVANTAGES	
	<ul> <li>Excellent adherence of the lubricant film to the metal even at high temperature.</li> <li>High anti-wear and EP properties: protects moving parts against wear and shocks.</li> <li>Very tough film: protects metal surfaces exposed to water, abrasive dust and corrosive fumes.</li> <li>Reduces noise and vibration.</li> <li>Film shows good elasticity at low temperature, avoiding any phenomena of cracking or spalling.</li> </ul>
HANDLING OPERA	TIONS - HEALTH - SAFETY

• CARTER ENS/EP 700 contains a flammable solvent: before it is applied, metal surfaces should be degreased to remove any abrasive particles or pollutants.

TYPICAL CHARACTERISTICS	METHODS	UNITS	CARTER ENS/EP 700
Density at 15 °C	ISO 3675	kg/m <sup>3</sup>	1000
Viscosity of dry extract at 100°C	ISO 3104	mm²/s	700
Viscosity with solvents at 25°C	ISO 3104		550
Softening temperature of dry extract	ASTM D 36	°C	45
Open cup flash point	ISO 2592	°C	< 55

Above characteristics are mean values given as an information.

TOTAL LUBRIFIANTS Industrie & Spécialités 11 june 2001 CARTER ENS/EP 700 1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or down loaded from <u>www.quick-fds.com</u>.